

Date 02 Sep 2014

TEST REPORT

Test No 1-00241454.B8

Brand:
SPANISH WOOL

Greasy Wool

Gross Mass : 0Kg
Declared Tare : 0Kg
Nett Mass : 0Kg

Total Bales : 1

Bale Numbers :

Yield Test Results

Wool Base (IWTO-19) (2 samples tested) : 40.01 %

Vegetable Matter Base (IWTO-19) : 1.5 %

(Including 0.00 % Hard Heads and Twigs)

Calculated Commercial Yields % Kg

IWTO Scoured Yield at 16% Regain 49.3

IWTO Schlumberger Dry 45.0

IWTO Scoured Yield at 17% Regain 49.7

IWTO Clean Wool Content 47.9

ASTM Clean Wool Fibre Present 46.5

Japanese Clean Scoured Yield @16% 47.1

Date 28 Aug 2014
Brand:
SPANISH WOOL

TEST REPORT
Laserscan (IWTO - 12)
Merino Wool

Test No 1-00241452.B2


Gross Mass : 0Kg
Declared Tare : 0Kg
Nett Mass : 0Kg

Total Bales : 0
Bale Numbers :

Results :

Laserscan (IWTO 12)

Mean Fibre Diameter : 26.9 um Coefficient of Variation : 21.60 %
Standard Deviation : 5.80 um % Fibres > 30 um : 24.58 %



KEMP FIBER = 0.2

For electronic verification go to <http://verify.wtaeurope.com> and enter the following code: **pal-61f-75s**

TEST REPORT

Length Report

Date 29 Aug 2014

Greasy Wool

Test No 1-00241453.B0

Brand:
SPANISH WOOL

Mass when sampled

0
0
0

Total Bales : 0

Results :

Mean Length : 116 mm

Standard Deviation : 24.50 mm

Coefficient of Variation : 21.10 %

