

Date 19 Sep 2014

**TEST REPORT**

Test No 1-00242268.B1

Brand:  
LOTE 1

Greasy Wool

Gross Mass : 0Kg  
Declared Tare : 0Kg  
Nett Mass : 0Kg

Total Bales : 1

**Yield Test Results**

Wool Base (IWTO-19)  
47.51 %  
( 2 samples tested )  
Vegetable Matter Base (IWTO-19)  
1.9 %  
(Including 0.10 % Hard Heads and Twigs)

Calculated Commercial Yields	%	Kg
IWTO Scoured Yield at 16% Regain	58.6	
<b><i>IWTO Schlumberger Dry</i></b>	<b>53.9</b>	
IWTO Scoured Yield at 17% Regain	59.2	
IWTO Clean Wool Content	56.9	
ASTM Clean Wool Fibre Present	55.2	
Japanese Clean Scoured Yield @16%	56.0	


**Laserscan (IWTO-12)**

Mean Fibre Diameter : 27.1 um  
( 4 specimens)

**ADDITIONAL INFORMATION...**

Coefficient of Variation : 23.90 %  
% Fibres > 30 um : 27.85 %

KEMP FIBER = 0.7 %



### TEST REPORT Length Report

Date 18 Sep 2014

Greasy Wool

Test No 1-00242267.B3

Brand:  
LOTE 1

Mass when sampled

0  
0  
0

Total Bales : 0

Results :

Mean Length : 169 mm

Standard Deviation : 21.40 mm

Coefficient of Variation : 12.70 %

